



**SILTECH CORPORATION**  
225 Wicksteed Avenue  
Toronto, Ontario, Canada, M4H 1G5  
(416)424-4567 (Tel) (416)424-3158 (Fax)

TECHNICAL DATA SHEET

**Silmer® OH Di-50**

Reactive Silicone Pre-polymer

**DESCRIPTION**

**Silmer® OH Di-50** is a linear di-functional silicone pre-polymer with reactive hydroxyl terminal end groups. It is used to modify various polymers in order to improve their surface and physical properties.

**TYPICAL PROPERTIES**

Appearance	Clear to hazy liquid
Colour, Gardner	1
Viscosity, cps	125
Active Content %	100
Solubility (1 % & 10%)	
-Water	Insoluble
-IPA	Soluble
-Aromatic Solvents	Soluble
Specific Gravity (25°C)	0.96
Hydroxyl Value	28
Molecular Weight	4,000
Equivalent Weight	1,980

**APPLICATION & USES**

**Silmer® OH Di-50** can be co-reacted into various polymers for coatings, plastics, resins and other applications to incorporate a silicone moiety into the polymer structure. When co-reacted during the polymerization stage, **Silmer® OH Di-50** improves the surface and physical properties of the polymer. These benefits include better slip, antiblocking, mar resistance, surface smoothness, flexibility and hydrophobicity. The hydroxyl functionality in **Silmer® OH Di-50** gives a permanent binding into the matrix of the polymers.

Typically **Silmer® OH Di-50** is reactive with polymers that contain the following reactive groups and or system:

- epoxide
- carboxylic acid
- esters
- isocyanates

Typical usage levels are between 1.0-3.0% wt.

**SHELF LIFE**

When stored in the original, unopened containers between 10 and 40°C, **Silmer® OH Di-50** has a shelf life of 36 months from date of manufacture.

**PACKAGING**

**Silmer® OH Di-50** is supplied in 20kg pails and 200kg drums.

**LEGAL DISCLAIMER**

Siltech Corporation believes that the information in this technical data sheet is an accurate description of the typical uses of the product. Siltech Corporation, however, disclaims any liability for incidental or consequential damages, which may result from the use of the product that are beyond its control. Therefore, it is the user's responsibility to thoroughly test the product in their particular application to determine its performance, efficacy and safety. Nothing contained herein is to be considered as permission or a recommendation to infringe any patent or any other intellectual property right.

**SILMER®** is a registered trademark of Siltech Corporation, Toronto, Ontario, Canada.